



TORELIEF Technical News - WS73HY3 -

■ Features and Benefits

Typical Applications	Metal Decor & Plastic Container
Features	Best High-definition reproducibility
	1) Better Image Reproducibility 2) Good ink transferability

■ Major Specifications

Model	WS73HY3
Total Thickness	0.73mm
Relief Depth	0.46mm
Base	Steel (0.25mm / Standard)
Hardness	Shore D 65
Wash out	Water / by Brush
Image Reproduction	(This data is not certified.)
Screen Range	1% - 98% / 200Lpi
Minimum Dot Size	φ=100um
Minimum Fine Line	20um

■ Processing Conditions

Item	Condition	Remark
Main Exposure	150 - 240sec	GS=17 solid, Tube fluorescent lamp 40W
Wash-out	80 - 110sec	Brush / 25°C
Drying	10min	50 - 60°C
Post Exposure	150 - 240sec	Lamp: Philips Actinic 40W(10R)

*1 : Above figures are not guaranteed value. It depends on the equipment conditions.

*2 : Wash-out water should be changed when wash-out time gets longer by about 30seconds (than initial wash-out time).